

What Is Claimed Is:

Sub A1

1. A method of etching a dielectric layer with selectivity to an underlying stop layer, comprising:
supporting a semiconductor substrate in a plasma etch reactor, the substrate including a dielectric layer over a stop layer;
supplying an etchant gas to the plasma etch chamber; and
etching openings in the dielectric layer by energizing the etchant gas into a plasma state, the etchant gas comprising a hydrogen-free fluorocarbon gas represented by C_xF_y gas wherein $y/x \leq 1.5$, an oxygen-containing gas and optional carrier gas.

2. The method of Claim 1, wherein the openings comprise vias, contacts, and/or trenches of a dual damascene structure, a self-aligned contact (SAC) structure or self-aligned trench structure.

3. The method of Claim 1, wherein the stop layer is silicon nitride and the etch rate selectivity of the dielectric to the silicon nitride is at least 10.

1 4. The method of Claim 1, wherein the dielectric layer comprises
2 doped or undoped silicon oxide layer or low-k material and the stop layer
3 comprises a silicon nitride layer.

1 5. The method of Claim 1, wherein the plasma etch reactor
2 comprises an ECR plasma reactor, an inductively coupled plasma reactor, a
3 capacitively coupled plasma reactor, a helicon plasma reactor or a magnetron
4 plasma reactor.

1 6. The method of Claim 1, wherein the plasma etch reactor
2 comprises a dual frequency capacitively coupled plasma reactor including an upper
3 showerhead electrode and a bottom electrode, RF energy being supplied at two
4 different frequencies to either the bottom electrode or at different first and second
5 frequencies to the showerhead electrode and bottom electrode.

1 7. The method of Claim 1, wherein the etchant gas is nitrogen-free,
2 the C_xF_y gas is at least C_4F_6 , the oxygen containing gas is at least O_2 and the
3 carrier gas is Ar, the etchant gas being supplied to the plasma etch reactor through
4 a showerhead electrode at flow rates of 2 to 50 sccm C_4F_6 , 2 to 50 sccm O_2 and 50
5 to 800 sccm Ar.

1 8. The method of Claim 1, wherein the C_xF_y gas is at least C_4F_6 , the
2 oxygen containing gas is at least O_2 and the carrier gas is Ar, the etchant gas being
3 supplied to the plasma etch reactor through a showerhead electrode at flow rates of
4 10 to 25 sccm C_4F_6 , 5 to 20 sccm O_2 and 50 to 300 sccm Ar.

1 9. The method of Claim 1, wherein a ratio of flow rates of the C_xF_y
2 to oxygen containing reactant is 0.5:1 to 5:1.

1 10. The method of Claim 1, wherein a ratio of flow rates of the C_xF_y
2 to oxygen containing reactant is 1:1 to 2:1.

1 11. The method of Claim 1, wherein pressure in the plasma etch
2 reactor is 10 to 200 mTorr and/or temperature of the substrate support is $-20^{\circ}C$ to
3 $+80^{\circ}C$.

1 12. The method of Claim 1, wherein pressure in the plasma etch
2 reactor is 50 to 100 mTorr and/or temperature of the substrate support is $+20^{\circ}C$
3 to $+60^{\circ}C$.

1 13. The method of Claim 1, wherein the plasma etch reactor is a
2 capacitively coupled plasma reactor having a powered showerhead electrode and/or

3 a powered bottom electrode, the showerhead electrode being supplied 0 to 3000
4 watts of RF energy and the bottom electrode being supplied 0 to 3000 watts of RF
5 energy.

1 14. The method of Claim 1, wherein the etchant gas includes CO
2 supplied to the plasma etch reactor at a rate of 50 to 500 sccm CO.

1 15. The method of Claim 1, wherein the C_xF_y is either C_4F_6 or C_6F_6 .

1 16. The method of Claim 1, wherein the C_xF_y is C_4F_6 and the oxygen
2 containing gas is O_2 , the C_4F_6 and O_2 being supplied to the plasma etch reactor at
3 flow rates having a ratio of $C_4F_6:O_2$ of 0.5:1 to 5:1.

1 17. The method of Claim 1, wherein the C_xF_y is C_4F_6 and the oxygen
2 containing gas is O_2 , the C_4F_6 and O_2 being supplied to the plasma etch reactor at
3 flow rates having a ratio of $C_4F_6:O_2$ of 1:1 to 2:1.

1 18. The method of Claim 1, wherein the C_xF_y is C_4F_6 and the oxygen
2 containing gas is supplied to the plasma etch chamber in an amount sufficient to
3 avoid etch stop during etching of the openings.

Sub
A2

19. The method of Claim 1, wherein the etched openings open onto flat and corner portions of the stop layer, the dielectric layer comprises BPSG and the stop layer comprises silicon nitride, the etch rate selectivity of the BPSG to the flat and corner portions of tyhe silicon nitride being at least 15.

20. The method of Claim 1, wherein the dielectric layer comprises BPSG and the stop layer comprises silicon nitride, the C_xF_y gas being C_4F_6 and the oxygen containing gas being O_2 , the C_4F_6 and O_2 being supplied to the plasma etch reactor at flow rates having a ratio of $O_2:C_4F_6$ of 0.5 to 1.2.

Add
A3